


MILITARY SPECIFICATION SHEET

WIRE, ELECTRIC, FLUOROPOLYMER-INSULATED, EXTRUDED ETFE,
 LIGHT WEIGHT, TIN-COATED COPPER CONDUCTOR, 600-VOLT, 150°C

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The complete requirements for procuring the wire described herein shall consist of this document and the issue in effect of Specification MIL-W-22759.



ETFE - Ethylene-Tetrafluoroethylene Copolymer

TABLE I. Construction details.

Part No. 1/	Wire size	Stranding (Number of strands X AWG gage of strands)	Diameter of stranded conductor (inches)		Finished wire		
			(min)	(max)	Resistance at 20°C (68°F) (ohms/1000 ft)	Diameter (inches)	Weight (lbs/1000 ft) (max)
					(max)		
M22759/18-26-*	26	19 X 38	.018	.020	41.3	.032 ± .002	1.52
M22759/18-24-*	24	19 X 36	.023	.024	26.2	.038 ± .002	2.12
M22759/18-22-*	22	19 X 34	.029	.031	16.2	.043 ± .002	3.18
M22759/18-20-*	20	19 X 32	.037	.039	9.88	.051 ± .002	4.76
M22759/18-18-*	18	19 X 30	.046	.049	6.23	.061 ± .002	7.10
M22759/18-16-*	16	19 X 29	.052	.055	4.81	(A) .070 ± .002	(A) 9.14
M22759/18-14-*	14	19 X 27	.065	.069	3.06	(A) .085 ± .002	(A) 14.1
M22759/18-12-*	12	37 X 28	.084	.089	2.02	(A) .107 ± .003	(A) 21.6
M22759/18-10-*	10	37 X 26	.106	.112	1.26	(A) .134 ± .003	(A) 34.1

1/ PART NO. : The asterisks in the part number column, Tables I and II, shall be replaced by color code designators in accordance with MIL-STD-681. Examples: Size 20, white - M22759/18-20-9; white with orange stripe - M22759/18-20-93.

(A) denotes changes

① TABLE II. Bend test mandrels and test loads.

Part No.	Mandrel diameter (inches) ($\pm 3\%$)		Test load (lbs) ($\pm 3\%$)	
	Life cycle test and short-term thermal stability test <u>1/</u>	Cold bend test	Life cycle test and short-term thermal stability test <u>1/</u>	Cold bend test
M22759/18-26-*	.50	.50	.25	0.5
M22759/18-24-*	.50	.50	.38	0.5
M22759/18-22-*	.75	.75	.38	1.0
M22759/18-20-*	.75	.75	.38	1.0
M22759/18-18-*	1.00	1.00	.50	1.0
M22759/18-16-*	1.00	1.00	.50	1.0
M22759/18-14-*	1.25	1.25	1.0	3.0
M22759/18-12-*	2.00	2.00	1.0	3.0
M22759/18-10-*	2.00	2.00	1.0	3.0

1/ Also for bend tests after immersion.

WIRE RATINGS AND ADDITIONAL REQUIREMENTS

TEMPERATURE RATING: 150°C (302°F) max conductor temperature

VOLTAGE RATING: 600 volts (rms) at sea level

SHORT-TERM THERMAL STABILITY: 7 hours at 230 $\pm 2^\circ\text{C}$ (446 $\pm 3.6^\circ\text{F}$). Quality conformance test, Group II; test procedure and requirements as in life cycle test except for time and temperature of oven exposure

ACID RESISTANCE: No requirement

BLOCKING: 200 $\pm 2^\circ\text{C}$ (392 $\pm 3.6^\circ\text{F}$)

COLOR: In accordance with MIL-STD-104, Class 1; white preferred.

COLOR STRIPING OR BANDING DURABILITY: 125 cycles (250 strokes) (min), 500 grams weight

DIELECTRIC TEST AFTER IMMERSION: 2000 volts (rms), 60Hz

① FLAMMABILITY: Vertical flame test (see page 3); 2 sec (max) after-flame; 5.50 in. (max) burn length
Post-flame dielectric test not required

HUMIDITY RESISTANCE: After humidity exposure, wire shall meet the requirements for initial insulation resistance.

IDENTIFICATION OF PRODUCT: Required. Shall be by ink printing only.

IDENTIFICATION DURABILITY: 125 cycles (250 strokes) (min), 500 grams weight

IMPULSE DIELECTRIC TEST: 8.0 kilovolts (peak), 100% test

INSULATION RESISTANCE, INITIAL: Sizes 26 through 20: 5000 megohms for 1000 ft (min)

Sizes 18 through 14: 3000 megohms for 1000 ft (min)

Sizes 12 through 10: 2000 megohms for 1000 ft (min)

LIFE CYCLE: Oven temperature, 200 $\pm 2^\circ\text{C}$ (392 $\pm 3.6^\circ\text{F}$)

Dielectric test, 2000 volts (rms), 60Hz

LOW TEMPERATURE (COLD BEND):

Bend temperature: -65 $\pm 2^\circ\text{C}$ (-85 $\pm 3.6^\circ\text{F}$)

Dielectric test, 2000 volts (rms), 60Hz

SHRINKAGE: 0.125 inch max at 200 $\pm 2^\circ\text{C}$ (392 $\pm 3.6^\circ\text{F}$)

SMOKE: 200°C (392°F)

SPARK TEST OF PRIMARY INSULATION: Not required

SURFACE RESISTANCE: Sizes 26 through 12: 500 megohm-inches (min), initial and final readings

Size 10: No requirement

THERMAL SHOCK: Oven temperature, 150 \pm 2°C (302 \pm 3.6°F)

Max change in measurement:

Sizes 26 through 12: 0.060 inch

Size 10: 0.100 inch

WICKING: No requirement

Ⓐ **WIRE LENGTH REQUIREMENTS:** Schedule A (See wire length schedules in MIL-W-22759)

WRAP TEST: "Wrap back" test required; no cracking

Oven temperature, 200 \pm 2°C (392 \pm 3.6°F)

INTENDED USE NOTE: The wire of this specification sheet is intended for hookup applications in electronic chassis. It is also intended for use in bundles under a protective jacket for inter-connecting applications; e. g., in airframes.

Ⓐ VERTICAL FLAME TEST

Apparatus - The flammability test chamber shall be approximately one foot square by two feet in height and shall be open at the top and front to provide adequate ventilation for combustion but prevent drafts. Inside the chamber, near the open top, a clamp shall be provided from which the wire specimen may be suspended vertically about six inches in front of the rear wall of the chamber and equidistant from the two sides. The test burner shall be a Bunsen type gas burner having a 1/4 inch inlet, a bore of 3/8 inch nominal, and a length of approximately 4 inches above the primary air inlets. The burner shall be capable of providing the specified test flame, which shall be a 3-inch flame with an inner cone approximately one third of the total flame height and a temperature, at its hottest portion, of 1010 \pm 56°C (1850 \pm 100°F) as measured by a thermocouple pyrometer.

Procedure - An 18 \pm 1/2 inch wire specimen, marked 14 \pm 1/2 inches from its upper end to indicate where the test flame is to be applied, shall be suspended in the vertical position in the chamber and a weight equal to that specified for life cycle test of the same wire shall be attached to the lower end of the specimen to keep it taut during the flame exposure. With the test flame adjusted as specified in the preceding paragraph and with the burner held upright but inclined 20 degrees from vertical toward the specimen, the hottest portion of the flame shall be applied for 15 seconds to the approximate position of the test mark on the wire and shall then be withdrawn. The duration of flaming in the specimen after withdrawal of the gas test flame shall be timed and recorded in seconds. The burn length on the specimen as indicated by burned, charred, or melted insulation shall be measured and recorded to the nearest 1/8 inch. Areas of the specimen having the original insulation undamaged but covered with soot deposit removable by wiping or covered with material which has melted and flowed down the wire shall not be considered as part of the burn length. Breaking of the wire specimen in size 24 or smaller shall not be considered as failure. If breaking occurs in 3 or more specimens, a 22-gage specimen may be substituted for purposes of this test.

Ⓐ **Metric Conversion Note:** Data in this specification sheet may be converted to metric as follows:

Linear dimensions	25.40 x inches = millimeters (mm)
Weight (general)	.4536 x lbs = kilograms (kg)
Wire weight	1.488 x (lbs/1000 ft) = kg/km
Conductor resistance	3.281 x (ohms/1000 ft) = ohms/km
Insulation resistance	.3048 x (megohms for 1000 ft) = megohms for 1 km
Surface resistance	25.00 x (megohm-inches) = megohm-millimeters

Custodians:

Navy - AS
Army - CR
Air Force - 85

Preparing activity:

Navy - AS
(Project No. 6145-0769)

Review activities:

Navy - OS, MC
Army - AR, AV, ME
Air Force - 99
DLA - IS
NSA

User activities:

Navy - EC
Army - AT
Air Force - 11


INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge (*DO NOT STAPLE*), and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE NAVY



NO POSTAGE
NECESSARY
IF MAILED
IN THE
UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE \$300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 12503 WASHINGTON D. C.

POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE NAVY

Commanding Officer
Naval Air Engineering Center
Engineering Specifications & Standards
Department (ESSD) Code 93
Lakehurst, NJ 08733



STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions - Reverse Side)

1. DOCUMENT NUMBER

2. DOCUMENT TITLE

3a. NAME OF SUBMITTING ORGANIZATION

4. TYPE OF ORGANIZATION (Mark one)

VENDOR

USER

MANUFACTURER

OTHER (Specify): _____

b. ADDRESS (Street, City, State, ZIP Code)

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER (Last, First, MI) - Optional

b. WORK TELEPHONE NUMBER (Include Area Code) - Optional

c. MAILING ADDRESS (Street, City, State, ZIP Code) - Optional

8. DATE OF SUBMISSION (YYMMDD)

(TO DETACH THIS FORM, CUT ALONG THIS LINE.)

DD FORM 1426
82 MAR

PREVIOUS EDITION IS OBSOLETE.